



# CMA Testing and Certification Laboratories

廠商會檢定中心

## TEST REPORT

Report No : AK011128-001

Date: 2008-04-09


Application No : LK210755

Applicant :

Buyer : Cheung Kee Canvas Ltd.

Sample Description : One (1) submitted piece of covering material in green colour stated to be 'PVC Tarpaulin Green Color' with Article No.: CK2009. \*\*\*

Sample Photo :



Date Received : 2008-04-02.

Test Period : 2008-04-02 to 2008-04-09.

Test Requested : Flammability test stated in the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988, Schedule 5 Part 1.

Test Method : As stated in the above specifications, the test was determined in accordance with BS 5852 : Part 1 : 1979 (Butane Flame Ignition Source 1).

Test Result : Refer to the results on page 2.

Conclusion : The submitted sample was found to comply with the requirements of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988 with amendments in 1989 and 1993 of United Kingdom, Schedule 5 Part 1.

For and on behalf of  
CMA Industrial Development Foundation Limited

Authorized Signature :

Keung Suet-Kwan, Sharon  
Specialist - Material & Packaging

Page 1 of 2

This document is issued subject to CMA Testing standard TERMS AND CONDITIONS, and shall not be reproduced except in full or with written approval by CMA Testing.

CMA Industrial Development Foundation Limited

Room 1302, Yan Hing Centre, 9-13 Wong Chuk Yeung St., Fo Tan, Shatin, N.T., Hong Kong.

Tel: (852) 2698 8198 Fax: (852) 2695 4177 E-mail: info@cmatel.com Web Site: http://www.cmatel.com



**TEST REPORT**

Report No : AK011128-001

Date: 2008-04-09

Application No : LK210755

Test Result :

Flammability test stated in the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988 with amendments in 1989 and 1993 of United Kingdom, Schedule 5 Part 1 (Ignition Source : 1).

Condition of test specimen : Temperature 20 ± 5°C Relative Humidity 50 ± 20%

Test Condition : Temperature 26°C Relative Humidity 60%

Criteria of Ignition	Specimen	
	1	2
<b>Progressive Smouldering criteria</b>		
a. Evidence of progressive smouldering in the interior and/or cover after 120 seconds of the removal of burner tube;	No	No
b. On final examination progressive smouldering is observed on the assembly dismantle and examined it internally.	No	No
<b>Flaming criteria</b>		
a. Evidence of flaming in the interior and/or cover after 120 seconds of the removal of burner tube.	No	No
<b>Result</b>	<b>Non-ignition</b>	

Fabric	Time to extinction after removal of burner			
	Flaming ceased time		Smoking ceased time	
	Min	Sec	Min	Sec
1 <sup>st</sup> test	/	/	/	5
Retest	/	/	/	6

- Remark:
- 1) The above test results relate only to the ignitability of the submitted sample with specific material, construction and treatment under the particular conditions of test.
  - 2) The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.
  - 3) The submitted sample was tested with standard non-fire retardant polyurethane foam as the filling material and subjected to water soaking procedure\* before being conditioned.  
\* The specimen was immersed in water in accordance with clauses 4.2 to 4.5 of BS 5651: 1978, at 40 ± 1 °C for 30 minutes and followed by flat dry.
  - 4) °C denotes degree Celsius  
% denotes percentage  
s denotes seconds

\*\*\*\*\* End of Report \*\*\*\*\*