

# TEST REPORT

NO.: A001T110104012001

Date: Jan 07, 2011

Page 1 of 2

**Applicant:** Cheung Kee Canvas Ltd.

**Address:** G/F.,352,Reclamation St.,Kln.,H.K.

**Report on the submitted sample said to be**

**Sample name:** CK 2008 High Yarn Strength

**Model:** 0.55mm×2.1m

**Item/Lot No. :** /

**Material:** PVC

**Buyer:** /

**Supplier:** /

**Manufacturer:** /

**Country of Origin:** /

**Country of Destination:** /

**Labelled Age Grading:** /

**Sample received date:** Jan 04, 2011

**Testing period:** From Jan 04, 2011 to Jan 07, 2011

## Testing Requested

For compliance with the European Standard on Safety of Toys:

-EN 71-3:1994+A1:2000 /AC: 2002- Migration of certain elements

## Conclusion

-EN 71-3: The submitted sample complied with the requirement.

\*\*\*\*\*FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S)\*\*\*\*\*

Written by:

Kelly

Tested by:

Irwin

Inspected by:

James

Approved by:

Jeena

# TEST REPORT

NO.: A001T110104012001

Date: Jan 07, 2011

Page 2 of 2

**Results:**
**EN 71-3:1994+A1:2000 /AC: 2002: Migration of certain elements**

Analysis was performed by inductively coupled plasma atomic emission spectrometer.

Soluble Element	Cadmium (Cd)	Lead (Pb)	Chromium (Cr)	Mercury (Hg)	Antimony (Sb)	Barium (Ba)	Arsenic (As)	Selenium (Se)
Limit	75	90	60	60	60	1000	25	500
Code	Specimen's testing result							
A	<5	<5	<5	<5	<5	14.4	<2.5	<5


**Specimen Description**

A: Green PVC

**Note:**

- unit: mg/kg=ppm, <=Less than.
- Results shown are of the adjusted analytical results.
- Photo is included.

Photograph of sample



CK 2008 High Yarn Strength

\*\*\*End of Report\*\*\*