

<b>Model No.</b> <b>CK15oz</b>	<b>High Tenacity Polyester PVC Laminated Fabrics</b>
<b>General Applications:</b>	Construction, Marine (Field) covers, Storage covers and many other applications
<b>Colors:</b>	Silver/Black, Silver/White, Silver/Yellow, Silver/Blue, Silver/Orange, Silver/Green
<b>Available Grades:</b>	Fire-Retardant, Ultra-Violet, Anti-Mildew, Anti-Cold
<b>Type of Products:</b>	Roll Type
<b>Flammability Test Method:</b>	Test method 2 of NFPA 701 2004



### Physical Properties:

<b>Fabric Detail</b> 網布規格	<b>1000D x 1000D x 20 x 22</b>			
<b>Item</b> 項目名稱	<b>Test Method</b> 執行標準	<b>Unit</b> 單位	<b>Value</b> 數據	
<b>Thickness</b> 厚度	<b>DIN53353</b>	<b>mm</b>	<b>0.543</b>	
<b>Total Weight</b> 總重量	<b>DIN53352</b>	<b>g/m<sup>2</sup></b>	<b>580.3</b>	
<b>Tensile Strength</b> 拉伸強度	<b>DIN53354</b>	<b>N/5cm</b>	經 Warp	<b>2526.6</b>
			緯 Weft	<b>2377.9</b>
<b>Elongation at Break</b> 斷裂伸張率	<b>DIN53354</b>	<b>%</b>	經 Warp	<b>19.7</b>
			緯 Weft	<b>21.7</b>
<b>Tear Strength</b> 撕裂強度	<b>DIN53363</b>	<b>N</b>	經 Warp	<b>410</b>
			緯 Weft	<b>361</b>
<b>Adhesion of coating Strength</b> 剝離負荷	<b>DIN53357</b>	<b>N/5cm</b>	經 Warp	<b>116.5</b>
			緯 Weft	<b>110.8</b>
<b>Remarks</b> 備註				

This technical data is offered as helpful suggestion only.  
It's accurate to the best of our knowledge at time of printing.