


|                                   |   |
|-----------------------------------|---|
| <b>Model No.</b><br><b>CK2008</b> | <b>High Tenacity Polyester PVC Laminated Fabrics</b>  |
| <b>General Applications:</b>      | Construction, Marine (Field) covers, Storage covers and many other applications                                 |
| <b>Colors:</b>                    | White, Yellow, Royal Blue, Sky Blue, Red, Orange, Brown, Grey, Black, Beige, Green, Dark Green, Deep Dark Green |
| <b>Available Grades:</b>          | Fire-Retardant, Ultra-Violet, Anti-Mildew, Anti-Cold  |
| <b>Type of Products:</b>          | Roll Type, Ready Made Size Type   |
| <b>Raw Material Origin:</b>       | From Japan  |
| <b>Flammability Test Method:</b>  | BS5867-2 2008 - Flammability  |



抗水  
Water  
Resistant



不變形  
Dimensional  
Stability



阻燃  
Flame  
Retardant



長壽命  
Long  
Lasting




抗紫外線  
UV  
Resistant



色牢度  
Color  
Fastness

### Physical Properties:



|                                      |                     |                  |             |      |
|--------------------------------------|---------------------|------------------|-------------|------|
| Fabric Detail<br>網布規格                | 500D x 500D 高強絲     |                  |             |      |
| Item<br>項目名稱                         | Test Method<br>執行標準 | Unit<br>單位       | Value<br>數據 |      |
| Thickness<br>厚度                      | DIN53353            | mm               | 0.55        |      |
| Total Weight<br>總重量                  | DIN53352            | g/m <sup>2</sup> | 518.4       |      |
| Tensile Strength<br>拉伸強度             | DIN53354            | N/5cm            | 經 Warp      | 2167 |
|                                      |                     |                  | 緯 Weft      | 2130 |
| Elongation at Break<br>斷裂伸長率         | DIN53354            | %                | 經 Warp      | 17.1 |
|                                      |                     |                  | 緯 Weft      | 24.7 |
| Tear Strength<br>撕裂強度                | DIN53363            | N                | 經 Warp      | 586  |
|                                      |                     |                  | 緯 Weft      | 362  |
| Adhesion of Coating Strength<br>剝離負荷 | DIN53357            | N/5cm            | 經 Warp      | 94   |
|                                      |                     |                  | 緯 Weft      | 98   |
| Remarks<br>備註                        |                     |                  |             |      |

#### Stock sizes 現貨尺寸:

|    |              |         |           |
|----|--------------|---------|-----------|
| 卷庄 | 2.1m x 50yds |         |           |
| 件庄 | 3m x 3m      | 3m x 6m | 3m x 6.8m |
|    | 3m x 12m     | 4m x 4m | 5m x 5m   |
|    | 5m x 10m     | 6m x 6m | 6m x 9m   |
|    | 7m x 7m      | 8m x 8m | 9m x 9m   |

This technical data is offered as helpful suggestion only.  
It's accurate to the best of our knowledge at time of  
printing.